

PCT


WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<p>(51) International Patent Classification ⁷ : B29C 51/14, 51/08</p>	<p>A1</p>	<p>(11) International Publication Number: WO 00/09313 (43) International Publication Date: 24 February 2000 (24.02.00)</p>
<p>(21) International Application Number: PCT/GB99/02589 (22) International Filing Date: 6 August 1999 (06.08.99) (30) Priority Data: 9817793.4 14 August 1998 (14.08.98) GB (71) Applicant (for all designated States except US): R.P. SCHERER CORPORATION [US/US]; Suite 200, 645 Martinsville Road, Basking Ridge, NJ 07920 (US). (72) Inventor; and (75) Inventor/Applicant (for US only): HEATH, Kenneth [GB/GB]; The Gables, Penllwyngwyn, Farm Drive, Bryn, Llanelli, Carmarthenshire SA14 9RR (GB). (74) Agent: HITCHCOCK, Esmond, Antony; Lloyd Wise, Tregear & Co., Commonwealth House, 1-19 New Oxford Street, London WC1A 1LW (GB).</p>	<p>(81) Designated States: AE, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZA, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).</p> <p>Published With international search report.</p>	

(54) Title: THE FORMATION OF INDICIA IN THE BASE OF A BLISTER PACK FOR TRANSFERENCE TO A BODY CAST THEREIN



(57) Abstract

In a process for creating one or more blisters in a blister film (4), indicia are formed in the base of the blister in the final stage of a single pass of the blister forming punch (2) or pin. The blister is cold formed by advancing the pin (2) in a direction transversely relative to the plane of the film (4), towards and into engagement with a platen carrying indicia-forming die (12). The end face of the pin is formed with a mould for indicia complementary to the die (2), and movement of the pin (2) towards the platen draws and stretches film (4) predominantly from around the blister, thereby minimizing stretching of the film (4) at the base of the blister.

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

- 1 -

THE FORMATION OF INDICIA IN THE BASE OF A BLISTER PACK
FOR TRANSFERENCE TO A BODY CAST THEREIN

This invention relates to the use of a laminated film to form blister packs in the blisters of which bodies are cast. Such blister packs typically comprise polymeric films in which the blisters are heat formed. The present invention is particularly concerned with the use of laminated films in which a metal foil is sandwiched between two polymeric layers.

Blister films are particularly suited for the casting of frangible bodies which comprise some pharmaceuticals. These bodies are commonly made using lyophilisation or freeze-drying processes, but alternative techniques such as those including a solid state dissolution stage are also used. The liquid material of the body is poured into the blister or blisters, and then subjected to various treatments while still in the blisters. The products remain in the blister until they are ready for use and at this stage they are readily extractable.

Polymeric blister films suffer from the disadvantage of being permeable, with the consequence that however well the individual blisters are sealed, there is always a potential storage problem if the contents of the blister must be protected from the surrounding atmosphere. With the above points in mind, laminated blister films have been developed in which a metal foil is sandwiched between polymeric films on either side. Such films are less permeable than all-polymeric films, but some known films can become distorted when subjected to heat treatments, generating irregularity in the cast products and making subsequent handling of the blister pack more difficult. Although some laminated films have been developed which are more stable under heat treatment; see our published European Patent Specification Nos. 0 646 367 and 0 710 101, generally these laminated films are not suitable for the hot-forming of blisters therein. The metal foil core, normally of

- 2 -

aluminium, is much better suited to cold forming.

There is currently a strong demand for products cast in blister films as described above to bear some indelible marking. To meet this demand, a hot formed blister can readily be adapted to bear indicia on its internal surface, which indicia are then reflected in the respective surface of the cast product.

In our International Patent Application filed today with priority from British Application Nos. 9717491.6 and 9718382.6, we have addressed the difficulties of creating indicia on the base of a blister formed with a laminated foil of the kind to which this invention relates simultaneously with the formation of the blister itself. In that Application, the problem is met by creating the indicia in the second stage of the two stage process in the first of which the blister itself is formed. According to the present invention, these two stages are accomplished in the single pass of the blister forming punch or pin by effectively controlling the manner in which the laminated film is stretched to form the blister. According to the invention, the blister is cold formed by advancing a pin in a direction transversely relative to the plane of the film towards and into engagement with a platen bearing an indicia-forming dye thereon. The end face of the pin is formed with a mould for the indicia complementary to the dye, and the movement of the pin towards the platen draws and stretches film predominantly from around the blister, thereby minimising stretching of the film at the base of the blister. As a consequence, the film at the base of the blister requires less recovery time before it is again stretched to form the indicia, which can thus be accomplished at the end of the single pass of the punch or pin.

In order to ensure that during the initial movement of the pin the film is stretched from around the blister rather than from the base thereof, a slightly greater frictional contact between the periphery of the end face of the pin and

- 3 -

the laminated film can be created. To some extent, this is accomplished by the formation of the mould in the pin end face, if around the mould the end face is substantially flat. However, the effect can be enhanced by forming the end face of the pin around the mould slightly concave whereby a peripheral edge is created which provides some additional grip.

The profile of the pin itself will of course also significantly influence the manner in which the film is stretched as the pin advances towards the platen. We have found that two or more contiguous frusto-conical sections are suitable, with the apex angle of the frusto-conical cone adjacent the end face being substantially 60° , and the apex angle of the frusto-conical section contiguous thereto being around 30° .

Another means by which the desired differential stretching of the film as the blister is formed can be achieved is by using a different material for the end face of the pin from that used for the flanks. Preferred materials for the punch or pin in methods of the invention are stainless steel or polytetrafluethylene (PTFE). When this variant is adopted, the punch or pin is formed in stainless steel which also forms the end face, with the flanks of the pin being coated with PTFE.

An embodiment of the invention will now be described by way of example and with reference to the accompanying drawings in which Figures 1 to 4 show the progressive stages in the formation of a blister in a laminated film of the kind to which the invention relates.

In Figure 1, a punch or pin 2 is shown over a laminated film 4 of the kind described in our published European Patent Specification Nos. 0647367 and 0710101, which film 4 comprises a metal foil with a polymeric layer on either side thereof. Towards the lower end of the pin 2 as shown, there are two contiguous frusto-conical flanks 6 and 8 leaning towards an end face 10 in which is formed the mould for indicia to be created in the base of the eventual

- 4 -

blister.

The film 4 is clamped in known manner, and as shown in Figure 2 the pin 2 advances thereagainst towards a platen 12 bearing an indicia forming dye thereon. During the initial stage shown in Figure 2 the stretching is relatively uniform, but the periphery of the end face 10 is of course making contact with the film 4 under progressively greater pressure. Thus, as the punch advances to its final position shown in Figure 3, the stretching at the base of the blister being formed is minimised, with film being stretched from the areas around the blister. As a consequence, indicia may be formed in the base of the blister as the blister is itself created, during the final movement of the punctual pin against the platen 12. This is typically within the last millimetre of movement of the punch or pin, normally within the last 0.3 to 0.5 millimetres thereof. Typical indicia will normally have a depth within these ranges.

Figure 4 shows the punch or pin 2 being withdrawn, and illustrates the resilient response of the laminated film which arises from the platen 12. It will be noted that the platen 12 and the surrounding base 16 which define the recess in which the blister is created do not themselves form a mould against which the laminated film is urged. The punch or pin 2 determines the entire shape of the blister itself, only the indicia are formed positively from both sides.

It should be understood that the invention applies to the application of indicia to be reflected in the respective surface of the cast product in the broadest sense of the term. Thus, any form of marking is included, and particularly marking having a purely functional purpose such as the creation of break lines. Break lines are commonly used on tablets for oral administration where there is an occasional need for only a portion of a tablet to be taken at a particular time. The invention thus has particular value in the formation in a face of a product cast in a blister pack of indicia or marking which takes the form of

- 5 -

or includes a break line. In this respect it will be appreciated that a break line can be effectively formed by a sequence of depressions or grooves; it does not have to be a continuous groove in all circumstances. What is important is that a line of weakness is formed which enables the cast product to be easily broken into two or more pieces as defined by the break line or lines.

CLAIMS

1. A method of forming a laminated film comprising a metal foil and a polymeric layer on either side of the foil with at least one blister the base of which bears projecting indicia for moulding into a body cast therein, which method comprises cold-forming the blister by advancing a pin in a direction transversely relative to the plane of the film towards and into engagement with a platen bearing an indicia-forming dye thereon, the end face of the pin being formed with a mould for the indicia complementary to the dye, wherein the movement of the pin towards the platen draws and stretches film from around the blister and minimises stretching of the film at the base of the blister.
2. A method according to Claim 1 wherein the end face of the pin is formed in a different material from that forming the flanks thereof.
3. A method according to Claim 1 or Claim 2 wherein the flank or flanks of the pin are shaped to progressively engage the film from the end face.
4. A method according to Claim 3 wherein the pin is formed with at least two contiguous frusto-conical sections adjacent the pin end face.
5. A method according to any preceding Claim wherein the end face of the pin around the mould is substantially flat.
6. A method according to any of Claims 1 to 4 wherein the end face of the pin around the mould is concave and forms a peripheral edge.




Fig 1




Fig 2




Fig 3




Fig 4

INTERNATIONAL SEARCH REPORT

International Application No.

PC1/G8 99/02589

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 B29C51/14 B29C51/08

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 B29C 865D A61J

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 5 457 895 A (THOMPSON ANDREW R ET AL) 17 October 1995 (1995-10-17) column 4, line 25 - line 34; figures 3,4 ---	1
A	EP 0 563 934 A (THOMAE GMBH DR K) 6 October 1993 (1993-10-06) column 6, line 19 - column 7, line 15; claim 14; figures 4,5 ---	1,6
A	WO 97 21534 A (ALUSUISSE LONZA SERVICES AG) 19 June 1997 (1997-06-19) claim 10 ---	1,3,5
A	EP 0 646 367 A (SCHERER LTD R P) 5 April 1995 (1995-04-05) cited in the application column 3, line 28 - line 33; figure 3 ---	
	--- -/--	



Further documents are listed in the continuation of box C.



Patent family members are listed in annex.

* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"Z" document member of the same patent family

Date of the actual completion of the international search

29 October 1999

Date of mailing of the international search report

09/11/1999

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 851 epo nl,
Fax: (+31-70) 340-3018

Authorized officer

Kosicki, T

INTERNATIONAL SEARCH REPORT

International Application No

PC1/GB 99/02589

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
P, X	EP 0 905 042 A (ALUSUISSE LONZA SERVICES AG) 31 March 1999 (1999-03-31) claim 10 -----	1, 3, 4

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PC1/GB 99/02589

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
US 5457895	A	17-10-1995	AU 7801494 A	01-05-1995
			CA 2149659 A	13-04-1995
			EP 0721325 A	17-07-1996
			JP 9506268 T	24-06-1997
			WO 9509608 A	13-04-1995
EP 0563934	A	06-10-1993	AU 3566193 A	07-10-1993
			CA 2093287 A	04-10-1993
			HU 68553 A	27-04-1995
			JP 6039020 A	15-02-1994
WO 9721534	A	19-06-1997	AU 703723 B	01-04-1999
			AU 7617196 A	03-07-1997
			CA 2192040 A	13-06-1997
			CN 1209089 A	24-02-1999
			EP 0779143 A	18-06-1997
			PL 326864 A	26-10-1998
			US 5879612 A	09-03-1999
EP 0646367	A	05-04-1995	US 5343672 A	06-09-1994
			GR 3023853 T	30-09-1997
			AT 153530 T	15-06-1997
			AT 165730 T	15-05-1998
			AU 677030 B	10-04-1997
			AU 5654594 A	22-06-1994
			BR 9305805 A	18-02-1997
			CA 2129254 A	09-06-1994
			CN 1089829 A	27-07-1994
			DE 69311109 D	03-07-1997
			DE 69311109 T	25-09-1997
			DE 69318429 D	10-06-1998
			DE 69318429 T	03-09-1998
			EP 0710101 A	08-05-1996
			ES 2102143 T	16-07-1997
			ES 2118368 T	16-09-1998
			FI 943537 A	27-07-1994
			WO 9412142 A	09-06-1994
			HK 1007489 A	16-04-1999
			HU 69435 A, B	28-09-1995
			JP 2796578 B	10-09-1998
			JP 8187271 A	23-07-1996
			JP 2568479 B	08-01-1997
			JP 7508676 T	28-09-1995
			NQ 942805 A	28-07-1994
			NZ 258600 A	21-12-1995
			US 5729958 A	24-03-1998
EP 0905042	A	31-03-1999	NONE	